



## Powdered Non Sterile Latex Examination Gloves

Kaltex Plus Powdered Non Sterile Latex Examination Gloves are made from Natural Rubber Latex. These gloves provide excellent barrier protection for both healthcare worker and patient.

### SAFETY FEATURES

- ▶ Enhanced elasticity, tear strength and donning.
- ▶ Beaded cuff with minimum length of 240 mm. Can offer 290 mm length also.
- ▶ Powdered with Modified Bio-Absorbable Corn starch, to prevent wound infections and granulomas.

### STANDARDS

- ▶ EN 455-1:2020, EN 455-2:2015, EN 455-3:2015 & ASTM D-3578:2019.
- ▶ Registered with USFDA (510K).

### QUALITY CONTROL

- ▶ Factory standard of 1.5 AQL for pinholes.

[www.kanamlatex.com](http://www.kanamlatex.com)



**Kanam**  
KANAM LATEX  
INDUSTRIES PVT. LTD.

The trusted name the world over

Ooppottil Buildings, K.K. Road  
Kottayam-686 001, Kerala, India  
Tel: 0481-2560108, 2563513  
Fax: 0481-2563614

E-mail: [customercare@kanamlatex.com](mailto:customercare@kanamlatex.com)  
[ho@kanamlatex.com](mailto:ho@kanamlatex.com)

# Product Information

## TYPE

Powdered Non Sterile Latex Examination Gloves

## PRIMARY MATERIAL

Natural Rubber Latex (NR).

## COLOUR

Creamy White.

## DESIGN

Ambidextrous, Straight Finger, Beaded Cuff, Smooth surface.

## POWDER AMOUNT

<10mg/dm<sup>2</sup>.

## SHELF LIFE

3 years in original packaging if stored as per storage instructions.



## PHYSICAL DIMENSIONS

Size	Length (mm) Min	Palm Width (mm)	Average weight per glove (gm)	Thickness (mm) Min	
				Palm	Finger
Small	240	84 - 85	4.5 - 5.0	0.08	0.08
Medium	240	95 - 96	5.0 - 5.5		
Large	240	106 - 107	5.5 - 6.0		
X-Large	240	112 - 113	6.0 - 6.5		

## PHYSICAL PROPERTIES

Characteristics	Before Ageing	After Ageing 100±2°C for 22±0.3hrs
Tensile Strength (Mpa) min.	20	18
Ultimate Elongation (%) min.	800	600
Force at break (N) Min.	6 During Shelf Life (N)	6 After Challenging (N)

## PRE-SHIPMENT QUALITY INSPECTION

**Sampling Procedure:** ISO 2859 Part I

**Sampling Plan:** Single sampling, Normal Inspection

Characteristics	Inspection Level	AQL
Freedom from Holes	G-1	1.5
Visual attributes – Major Defects	G-1	1.5
Visual attributes – Minor Defects	G-1	2.5
Physical Dimension	S-2 / N=13	4.0
Physical Properties	S-2	4.0
Force at break N=13	N/A	
Extractable Protein Content	N=3	N/A
Powder free residue	N=5	N/A

## PACKAGING

Material	Quantity	Dimension (cm)
Inner Box	100 Pcs.	22(L) x 11(W) x 6.5(H)
Master Carton	2000 Pcs.	45.5(L) x 34.5(W) x 22.5(H)



Powdered Non Sterile Latex Examination Gloves